



(586) 948-9920 | www.rapiddiecut.com

KLINGERSIL C-4401

KLINGERSIL C-4401 is a universal gasket material for use in a wide range of applications. This general purpose gasket material has excellent sealability and chemical resistance.

This material is manufactured with aramid fiber reinforced with a nitrile binder.

Typical Values Refer To 1/16" Thick Material Unless Noted

Creep Relaxation ASTM F38B (1/32")	20%
Sealability ASTM F37A (1/32")	< 0.25 ml/hr
Gas Permeability DIN 3535/6	< 0.5 ml/min
Compressibility ASTM F36J	7-14%
Recovery ASTM F36J	50% Minimum
KLINGER Hot Compression Test Thickness Decrease 73F (23C) Thickness Decrease 572F (300C)	14% Initial 17% Additional
Weight Increase ASTM F146 after immersion in Fuel B, 5h/73F (23C)	10% Maximum
Thickness Increase ASTM F146 after immersion in ASTM Oil IRM 901, 5h/300F (149C) ASTM Oil IRM 903, 5h/300F (149C) ASTM Fuel A, 5h/73F (23C) ASTM Fuel B, 5h/73F (23C)	0-5% 0-5% 0-5% 0-10%
Dielectric Strength ASTM D149-95a	14 kV/mm
Density ASTM F1315	112 lb/ft ³ (1.8g/cc ³)
Leachable Chloride Content FSA Method	100 ppm
ASTM F104 Line Call Out	F712121B3E12K6M5
Color	Green or White