



Density 4.0 pcf (64.1 kg/m³)
Maximum Loading 5.0 psi (34.5 kPa)
Color Black, Natural



ETHAFOAM™
packaging products

ETHAFOAM™ 400 Polyethylene Foam

ETHAFOAM™ 400 polyethylene foam (same as ETHAFOAM™ HS-45) is a strong, resilient, high-density 4.0 pcf (64.1 kg/m³), closed-cell foam. It is ideally suited as a component material in products requiring a shock absorbing, vibration dampening, insulating, barrier and/or buoyancy component, and as a material for cushioning components in packaging applications for loadings up to 5.0 psi (34.5 kPa).

ETHAFOAM 400 has outstanding dimensional stability and recovery characteristics that provide optimal cushioning protection against repeated impacts. It is ideal for cushion packaging and is used in many applications, including computer, automotive, construction and recreation. To achieve optimum performance, Dow recommends that qualified packaging engineers design the total packaging solution.

Sizes Available in Black (Planks):

2" x 24" x 108"
4" x 24" x 108"

Sizes Available in Natural (Planks):

2" x 24" x 108"
3" x 24" x 108"

Product Features

ETHAFOAM™ 400 polyethylene foam is a durable, lightweight, flexible, solid extruded product. As the properties listed on the reverse suggest, ETHAFOAM 400 offers excellent strength, resistance to creep under load, vibration and shock absorbency, and water resistance characteristics.

ETHAFOAM 400 is produced with Dow's patented *RapidRelease* manufacturing process. *RapidRelease* technology delivers a higher quality product with improved dimensional stability and safety. This process technology incorporates a patented CFC- and HCFC-free blowing agent system and an accelerated curing system that reduces residual blowing agents in ETHAFOAM products to trace amounts.

ETHAFOAM 400 meets the requirements of the U.S. Clean Air Act Amendments. It is easily fabricated, impervious to most chemicals, non-abrasive and performs consistently over a wide range of temperatures.

ETHAFOAM 400 is also reusable and completely recyclable because it is made of non-crosslinked polyethylene.

Flammability

ETHAFOAM™ 400 polyethylene foam has successfully passed FMVSS 302 flammability testing, conducted according to the U.S. Code of Federal Regulations, CFR 49.

ETHAFOAM
Product Information

| Physical Properties of ETHAFOAM™ 400 Polyethylene Foam | | | |
|--|---|-----------|--|
| Physical Properties ¹ | Test Method | Direction | Value |
| Density | ASTM D3575, Suffix W, Method B; ISO 845 | | pcf (kg/m ³) 4.0 (64.1) |
| Compression Set | ASTM D3575, Suffix B (50% compr.) | Vertical | < 15% |
| Compressive Creep (1000 hrs @ 73°F [23°C]) | ASTM D3575, Suffix BB | Vertical | < 10% @ 5.0 psi (34.5 kPa) |
| Compressive Deflection @ 10% @ 25% @ 50% | ASTM D3575, Suffix D | Average | psi (kPa) 17 (117) 19 (131) 32 (221) |
| Thermal Stability | ASTM D3575, Suffix S | | < 1% |
| Thermal Conductivity @ 75°F (24°C) @ 23°F (-5°C) | ASTM D3575, Suffix V; EN 28301; ISO 2581 | Vertical | BTU•in/hr•ft ² •°F (W/m ² K) 0.42 (0.06) 0.37 (0.05) |
| Water Absorption | ASTM D3575, Suffix L; ISO 2896; ASTM C272 | | lb/ft ² (kg/m ²) 0.2 (1.0) < 1% by volume |
| Buoyancy | ASTM D3575, Suffix AA | | pcf (kg/m ³) 58 (930) |
| Tensile Strength @ peak | ASTM D3575, Suffix T; ISO 1798 | Average | psi (kPa) 50 (345) |
| Tensile Elongation | ASTM D3575, Suffix T; ISO 1798 | Average | 70% |
| Tear Strength | ASTM D3575, Suffix G | Average | lb/in (N/mm) 19 (3.7) |

¹The data presented for this product are for unfabricated ETHAFOAM polyethylene foam products. While values shown are typical of the product, they should not be construed as specification limits.

For information on products, design assistance and testing services available from Dow, contact us at: 1-866-PKG-FOAMS (754-3626) or www.ethafoam.com

NOTICE: No freedom from any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

WARNING: ETHAFOAM polyethylene foam products are combustible and may constitute a fire hazard if improperly used or installed. During transportation, storage, installation and use, these products should not be exposed to open flame or other ignition sources.

ETHAFOAM PACKAGING PRODUCTS
THE DOW CHEMICAL COMPANY
P.O. Box 1206 • Midland, MI 48641-1206 • USA
www.ethafoam.com

