



Product: Diamondback

Construction: Spun Bond – Thermal Set

Composition: Polypropylene

Finish: Heat set, Diamond Pattern

Weight: 2 oz/sq. yd.

Thickness: Approximately .014” +/- .005”

Color: Black, White

Width: 60” +/- 1”

Flammability: FMVSS302

Property	Test Method	Units	Average	StDev
Basis Weight	ASTM D3776-09	opsy	2.01	.02
MD Tensile@ Peak	ASTM D5034-09	lbs	48.7	1.15
CD Tensile @ Peak	ASTM D5034-09	lbs	42.14	1.47
MD Elongation @ Peak	ASTM D5034-09	%	71.62	.26
CD Elongation @ Peak	ASTM D5034-09	%	83.95	4.17
MD Trap Tear	ASTM D4533-91	lbs	23.38	1.76
CD Trap Tear	ASTM D4533-91	lbs	17.91	1.82
Width is in spec			yes	