

SAE Spec. No.	THICKNESS		WEIGHT		Density % Specific Gravity	Actual Wool Content (Min.) %	Carbon Tetra-Chloride Soluble (Max.) %	Water Soluble (Max.) %	Combined Carbon Tetra-Chloride and Water Soluble (Max.) %	Ash (Max.) %	Tensile Strength (Min.) PSI	Splitting Resistance (Min.) Lbs. Per 2" Width	Standard Width Color
	Nominal Inch	Limits Inch	Nominal Lbs. Per Square Yard	Limits Lbs. Per Square Yard									
F-1 16R1	1/8 3/16 1/4 5/16 3/8 1/2 5/8 3/4 7/8 1	0.113-0.137 0.175-0.201 0.236-0.264 0.298-0.328 0.359-0.391 0.481-0.519 0.603-0.647 0.725-0.775 0.847-0.903 0.969-1.031	2.0 3.0 4.0 5.0 6.0 8.0 10.0 12.0 14.0 16.0	1.90-2.10 2.85-3.15 3.80-4.20 4.75-5.25 5.70-6.30 7.60-8.40 9.50-10.50 11.40-12.60 13.30-14.70 15.20-16.80	34.2	95	2.5	2.5	3.0	1.5	500	33	60" White
F-2 16R2	-	-	-	-	34.2	95	2.5	2.5	4.0	2.0	500	28	60" Except Gry or Blk
F-3 16R3	1/8 3/16 1/4 5/16 3/8 1/2 5/8 3/4 7/8 1	0.113-0.137 0.175-0.201 0.236-0.264 0.298-0.328 0.359-0.391 0.481-0.519 0.603-0.647 0.725-0.775 0.847-0.903 0.969-1.031	1.95 2.93 3.90 4.87 5.85 7.80 9.75 11.70 13.65 15.60	1.80-2.10 2.71-3.15 3.61-4.19 4.50-5.24 5.41-6.29 7.21-8.39 9.01-10.49 10.81-12.59 12.61-14.69 14.41-16.79	33.3	90	2.5	3.0	4.5	2.5	400	22	60" Grey
F-5 12R1	1/8 3/16 1/4 5/16 3/8 1/2 5/8 3/4 7/8 1	0.111-0.139 0.172-0.204 0.232-0.268 0.293-0.333 0.353-0.397 0.474-0.526 0.595-0.655 0.716-0.784 0.837-0.913 0.958-1.042	1.53 2.29 3.06 3.82 4.59 6.12 7.65 9.18 10.71 12.24	1.45-1.61 2.17-2.41 2.90-3.22 3.62-4.02 4.35-4.83 5.80-6.44 7.25-8.05 8.70-9.66 10.15-11.27 11.60-12.88	26.2	95	2.5	2.5	3.0	2.0	400	18	60" White
F-6 12R2	-	-	-	-	26.2	92	2.5	2.5	4.5	2.5	275	16	60" or 72" Grey
F-7 12R3	-	-	-	-	26.2	80	3.0	4.0	7.0	3.0	250	12	72" Grey
F-10 9R1	1/8 3/16 1/4 5/16 3/8 1/2 5/8 3/4 7/8 1	0.105-0.145 0.165-0.211 0.224-0.276 0.284-0.342 0.343-0.407 0.462-0.538 0.581-0.669 0.700-0.800 0.819-0.931 0.938-1.062	1.06 1.59 2.12 2.65 3.18 4.24 5.30 6.36 7.42 8.48	0.98-1.14 1.47-1.71 1.96-2.28 2.45-2.85 2.94-3.42 3.92-4.56 4.90-5.70 5.88-6.84 6.86-7.98 7.84-9.12	18.1	95	2.5	2.5	3.0	2.5	225	8	72" White
F-11 9R2	-	-	-	-	18.1	92	3.0	2.5	4.5	3.0	200	6	72" Grey
F-12 9R3	-	-	-	-	18.1	85	4.0	2.5	6.5	3.5	100	3	72" Grey
F-13 9R4	-	-	-	-	18.1	75	4.0	4.0	8.0	3.5	75	2	72" Grey
F-15 9R5	-	-	-	-	18.1	55	4.0	5.0	9.0	4.0	75	2	72" Grey
F-26 8R5	1/8 1/4 3/8 1/2 3/4 1	0.085-0.165 0.194-0.306 0.303-0.447 0.412-0.588 0.630-0.870 0.848-1.152	0.90 1.80 2.70 3.60 5.40 7.20	0.81-0.99 1.62-1.98 2.43-2.97 3.24-3.96 4.86-5.94 6.48-7.92	15.4	45	8.0	6.0	14.0	5.0	-	-	72" Grey
F-50 16R1X	3/64 1/16 5/64 3/32	0.040-0.054 0.056-0.070 0.071-0.085 0.087-0.101	0.750 0.975 1.200 1.425	0.712-0.788 0.937-1.013 1.162-1.238 1.387-1.463	33.3	95	2.5	2.5	3.0	1.5	500	-	60" or 72" White
F-51 16R3X	-	-	-	-	33.3	92	2.5	2.5	4.5	2.5	300	-	60" or 72" Grey
F-55 12R3X	1/16 3/32	0.056-0.070 0.087-0.101	0.750 1.125	0.712-0.788 1.087-1.163	25.6	75	4.0	4.0	8.0	3.0	200	-	60" or 72" Gry or Blk