



200 Founders Dr.
Woonsocket, RI 02895
Phone: 401-765-2340
Fax: 401-765-4915

FLOCK TEX FT-5581 Natural Auto Cloth

Meets: GM6420, Type 1 B
MATERIALS TEST DAT for 2019

A. Construction	Flock Fiber	100% Nylon 1.5/3.0 Denier 0.020 – 0.050” length
B. Abrasion Resistance	Wet (CS-10/500g) Dry (CS-10/1000g) Heat aged (7 days@82C) (CS-10/1000g)	1000 cycles 1500 cycles 1500 cycles
C. Fogging	SAE J1756-94	90 + Units
D. Xenon	SAE J1885-92 (225KJ-144hrs)	PASS
E. Flammability	GM 6090M-99(GM 9070P-96) ISO 3795-89	PASS (CERTIFIED)
F. Odor	SAE J1351(93)	PASS
G. Composition	28.2% Polyester-Fabric 15.2% Cotton-Fabric 28.3% Acrylic Latex 28.3% Nylon Flock (2 ounces per square yard)	
H. Weight	7.0 – 7.5 ounces per square yard	
I. Thickness	0.028 – 0.032 inches	16 oz. & ¼” diameter foot
J. Compliance	European Union (EU), RoHS, REACH, California Proposition 65	

Warranty

No warranties are made in this bulletin. All information, recommendations and descriptive material concerning Flock Tex, Inc. products are based upon research which is believed to be reliable but shall not constitute a warranty. Accordingly, all Flock Tex, Inc. products are sold with the understanding that purchasers will be solely responsible for determining the suitability of the materials for any purpose. Data presented are typical physical properties and are taken from a limited number of production runs, and they should not be used for specification purposes.