



**FORT  
WAYNE  
SPECIFICATIONS**

ISSUED	9/25/1997
REVISED	12/4/2017
REVISION	5
PAGE	1 of 1
APPROVAL	<i>Jacob Honkomp</i> <b>Jacob Honkomp</b>

**Z65MC - Charcoal**

<b>Test</b>	<b>Minimum</b>	<b>Maximum</b>	<b>Units</b>
Pore (Pressure Drop)	60	70	ppi
Density	1.75	2.05	lbs/ft <sup>3</sup>
Tensile	25.0		psi
Elongation	225		%
Tear	3.0		lbs/in
CFD 25%R(2"x2"x1")	0.35		psi
CFD 65%R(2"x2"x1")	0.55		psi
Compression Set 50%		15	%

Disclaimer: This certification is being provided electronically as a matter of convenience to our customers. Tampering with this document is strictly prohibited. The original document is on file in FXI's offices located in Fort Wayne, IN, and is available for inspection upon request.